

EXPOSURE PATTERN OR MASK AND INSPECTION METHOD AND MANUFACTURE
METHOD FOR THE SAME

Cross Reference To Related Applications

5 [0001]

The present document is based on Japanese Priority Document JP2003-043449, filed in the Japanese Patent Office on February 21, 2003, the entire contents of which being incorporated herein by reference.

10

Background of the Invention

[0002]

1. Field of the Invention

15 The present invention relates to an exposure pattern or mask suitable for use in an electron beam exposure process, and to an inspection method and manufacture method for an exposure pattern or mask.

[0003]

2. Description of Related Art

20 Miniaturization of recent semiconductor devices advances further and exceeds the limit of a resolution of an optical lithography system. In order to overcome this, fine patterning techniques have been developed which use a charged particle beam such as an electron beam and an ion beam to expose
25 and draw a micro circuit pattern.

[0004]

30 A conventional direct drawing method utilizing electron beam exposure is, however, requires a large amount of data when micro patterns are used for an LSI (large scale integrated) circuit having a high integration density. This results in a long drawing time and a low productivity

(throughput) .

[0005]

In order to address this drawback, an electron beam aligner or an ion beam aligner has been proposed which aligner
5 irradiates an electron beam or an ion beam to a transfer mask to form a circuit pattern on a wafer with the beam passed through through holes (pattern openings) of the transfer mask.

[0006]

Exposure techniques of this type include: for
10 example, an electron beam projection lithography using a high energy electron beam (refer to EPL: Electron-beam Proximity Lithography, H. C. Pfeiffer, Jpn. J. Appl. Phys. 34, 6658 (1995)); a low energy electron beam proximity projection lithography using a low energy electron beam (refer to LEEPL:
15 Low Energy Electron-beam Proximity Projection Lithography, T. Utsumi, U. S. Patent No. 5,831,272 (3, November 1998)); an ion beam projection lithography using an ion beam (refer to IPL: Ion-beam Lithography, H. Loeschner et al., J. Vac. Sci. Technol. B19, 2520 (2001)); and other techniques.

20 [0007]

An electron beam transmission mask (projection mask) used with these aligners, e.g., an LEEPL stencil mask, has the structure such as shown in a plan view of Fig. 10A and a cross sectional view of Fig. 10B taken along line X-X' shown in Fig. 10A. This stencil mask 67 has a membrane (thin
25 film) having a thickness of 100 nm to 10 μ m and formed with pattern openings 59. For example, the membrane (thin film) 51 of the stencil mask 67 having a thickness of 100 nm to 10 μ m in thickness has a plurality of through holes (pattern openings) 59 having a width of 0.03 μ m to 0.04 μ m through which
30 an electron beam is transmitted. In Figs. 10A and 10B, only

several pattern openings 59 are drawn for the purposes of drawing simplicity. The membrane 51 is supported by a silicon (Si) wafer (support substrate) 56. The Si wafer 56 is formed on an SiO₂ film 55 formed around and outside the pattern openings 59 and having an opening 61 of 20 to 40 mm in diameter and has an opening 60 larger in size than the opening 61 of the SiO₂ film 55.

[0008]

As shown in Fig. 11, in an exposure process using the stencil mask 67, for example, the stencil mask 67 is disposed on a photoresist layer 57 formed on a wiring material layer 54 to be patterned, the wiring material layer being formed on an SiO₂ film 55 on a semiconductor substrate 58. In this state, an electron beam 71 is emitted and passed through the pattern openings 59 of the membrane 51 of the stencil mask 67 to expose the photoresist layer 57 in a predetermined pattern. A photoresist pattern 57 left through development is used as a mask to dry etch the wiring material layer 54 and form a wiring pattern.

[0009]

If the stencil mask 67 has, for example, a rectangular ring pattern opening 59 such as shown in Fig. 12A, a central area 51a serving as an electron beam absorber area falls out and cannot maintain the pattern opening. If the stencil mask has a leaf-shaped opening pattern (not shown), the shape of the opening pattern cannot be maintained stably because this opening pattern is of a cantilever structure. These pattern openings are unable to be formed or difficult to be formed.

[0010]

In order to form an object pattern opening 59 on

a wafer, a so-called complementary division method has been introduced. Namely, the pattern opening 59 is geometrically divided into two masks 67A and 67B having divided opening patterns 59A and 59B, respectively, as shown in Fig. 12B and complementarily overlaid on the wafer as shown in Fig. 12C.
[0011]

Figs. 13A to 14C illustrate a process of fabricating the stencil mask 67. As shown in Fig. 13A, on an Si wafer (support substrate) 56, an SiO₂ film 55 and a membrane 51 made of Si or SiC are sequentially deposited to predetermined thicknesses.
[0012]

As shown in Fig. 13B, a resist layer 63 having a predetermined pattern is formed on the Si wafer 56. A partial region of the Si wafer 56 is removed down to the surface of the SiO₂ film 55 by dry etching to form an opening 60 and a support column 70 which partitions each mask quadrant.
[0013]

As shown in Fig. 13C, after the resist pattern 63 is removed, by using the Si wafer 56 and support column 70 as a mask, a partial region of the SiO₂ film 55 is removed down to the surface of the membrane 51 by dry etching to form an opening 61.
[0014]

As shown in Fig. 14A in the up-side-down state of Fig. 13C, a resist layer 63 is formed on the membrane 51 and processed to have a predetermined pattern.
[0015]

More specifically, openings 64 are formed through the membrane 51 to form a mask pattern portion 62 above the openings 60 and 61.

[0016]

Next, as shown in Fig. 14B, by using the resist pattern 63 as a mask, the membrane 51 is dry etched to form through holes in the area corresponding to the mask pattern portion 62 to thereby form mask pattern openings 66.

[0017]

Thereafter, as shown in Fig. 14C, the resist pattern 63 on the membrane 51 is removed so that a stencil mask 67 can be formed.

10 [0018]

It is important to inspect whether the stencil mask has the pattern openings 66 just as designed.

[0019]

In one example of a mask inspection apparatus and method, it is possible to inspect whether there is any defect of a mask, by utilizing an electron beam aligner without utilizing an additional inspection apparatus. {Refer to Patent Document 1: Japanese Unexamined Patent Publication No. 2001-153637 (p. 3, 28-th line in right column to p. 5, 2-nd line in right column, Fig. 2)}

20 [0020]

In another example of a mask inspection apparatus and method, a mask pattern defect is inspected in the following manner. A mask pattern to be inspected is two-dimensionally scanned with an electron beam to obtain mask pattern transmission electric signals. From these electric signals, a mask pattern signal corresponding to the shape of the mask pattern is obtained. This mask pattern signal is compared with a CAD (Computer Aided Design) signal corresponding to a CAD figure to be used for mask pattern fabrication, and basing upon this comparison result, a mask pattern defect is inspected.

{Refer to Patent Document 2: Japanese Unexamined Patent Publication No. 2002-71331 (p. 3, 49-th line in left column to p. 4, 21-st line in right column, Fig. 1))

[0021]

5 Another inspection uses a reticle (optical mask or photomask) and its layout method of the following type. For example, each of a plurality of shots constituted of a plurality of different chips is disposed on a reticle in such a manner that all or some of chips having the same pattern are aligned
10 along a row or column direction or directions to inspect the mask. {Refer to Patent Document 3: Japanese Unexamined Patent Publication No. HEI-10-73916 (p. 3, 41-st line in left column to p. 4, 3-rd line, Fig. 1)}

15 Summary of the Invention

[0022]

 In both the inspection methods described in Patent Document 1 (Japanese Unexamined Patent Publication No. 2001-153637) and Patent Document 2 (Japanese Unexamined Patent
20 Publication No. 2002-71331), a stencil mask is inspected by a "Die to Data" method by which a pattern image of pattern openings is detected by irradiating an electron beam to the stencil mask and thereafter the pattern image is compared with design CAD data or the like. With these methods, however,
25 since the data amount is large, the inspection takes a long time. In addition, since comparison evaluation of the real pattern is performed by using the data in a database, this approach is indirect and not accurate.

[0023]

30 Detailed and particular LEEPL stencil mask inspection methods and apparatuses are still not established

yet.

[0024]

In the meantime, it is necessary to prepare a dedicated reticle inspection apparatus for a reticle inspection. The Reticle inspection methods include a chip comparison inspection method by a "Die to Die" method and a chip - data comparison inspection method by a "Die to Data" method which inspects a reticle through comparison between a real mask pattern and design CAD data or the like.

10 [0025]

The chip comparison inspection method disclosed in Patent Document 3 (Japanese Unexamined Patent Publication No. HEI-10-73916) inspects a reticle (optical mask) by the Die to Die method. This method can inspect a reticle only if shots contain the chips having the same pattern.

15 [0026]

Since this comparison inspection method requires to align the chips having the same pattern along the row or column direction, the degree of freedom of the chip layout on a mask is lowered.

20 [0027]

As different from a reticle, a stencil mask for LEEPL or the like uses a silicon wafer same as that used for manufacturing semiconductor devices. There is therefore a high possibility that inspection can be performed by using a general silicon wafer inspection apparatus. If a wafer defect inspection apparatus widely used in inspecting a semiconductor device can be used for the inspection of stencil masks for LEEPL or the like, it presents large merits in terms of data reliability and availability to both the wafer and mask inspection apparatuses.

[0028]

Exposure using a stencil mask is of an equal magnification projection type. Because of the restrictions such as a mask pattern size, it is difficult to perform a
5 comparison inspection by the Die to Die method.

[0029]

This difficulty will be detailed. As shown in Fig. 15, a stencil mask 67, for example, for LEEPL, has a mask pattern portion 62 made of a membrane (thin film) 51 formed in a central
10 area of an Si wafer (support substrate) 56 having a size of, for example, 4 to 8 inches.

[0030]

The mask pattern portion 62 (membrane 51) is the area in and toward which an electron beam can be irradiated
15 reliably. This area is defined in a range of, for example, about 4 cm square and partitioned into four sections: a first quadrant 52A, a second quadrant 52B, a third quadrant 52C and a fourth quadrant 52D. One sectional area corresponds to the area of one chip. Stepper exposure of an electron beam is
20 executed by moving the stencil mask 67 relative to an exposure object (semiconductor substrate) sequentially from the first quadrant 52A to fourth quadrant 52D.

[0031]

Exposure by an electron beam is therefore four
25 cumulative shot exposure in total. The size of one shot (one chip) corresponds, therefore, to each area of the first quadrant 52A, second quadrant 52B, third quadrant 52C and fourth quadrant 52D, i.e., a one fourth area (about 2 cm square) of the membrane 51 (mask pattern portion 62).

30 [0032]

Under this circumstance, it is probably difficult

in terms of size to dispose a plurality of dies (semiconductor chips) having the same pattern in the one shot small area (quadrant) of about 2 cm square and to perform inspection by the Die to Die method. Namely, the comparison inspection by the Die to Die method is difficult unless three or more dies are formed in one shot.

[0033]

If the die has a size of, for example, about 7 mm square or smaller whose side length is one third of that of about 2 cm square, it is possible to dispose three or more dies having the same pattern in one quadrant. Demands for chips having such a small size are, however, reducing in practical use.

[0034]

If a plurality of dies cannot be disposed in one shot of the mask pattern portion 62 (i.e., if the comparison inspection by the Die to Die method is impossible), inspection of an LEEPL stencil mask utilizing a wafer defect inspection apparatus is not easy. Although this problem is irrelevant to the Die to Data method, comparison inspection by this method is more indirect than the Die to Die method and a direct and accurate inspection of a real pattern is not possible.

[0035]

The present invention has been made under the above-described circumstances. According to an embodiment of the present invention, there is provided an exposure pattern or mask inspection method capable of performing an exposure pattern or mask comparison inspection with ease and at a high precision, its manufacture method, and an exposure pattern or a mask.

[0036]

The present invention relates to an inspection method for an exposure pattern or mask, to an exposure pattern or mask manufacture method adopting the inspection method of this kind, and to an exposure pattern or mask having inspection pattern portions. The manufacture and inspection method of manufacturing and inspecting an exposure pattern or mask for exposing a predetermined pattern by an exposure beam, including the steps of: disposing a plurality of inspection pattern portions (particularly dummy inspection pattern portions to be described later: the same reference is applied hereinafter) having the same pattern as at least a part of a mask pattern portion, inside and/or outside an area of the mask pattern portion of the exposure pattern or mask (e.g., LEEPL stencil mask pattern or mask: the same reference is applied thereinafter); and comparing one or more of the inspection patterns with at least the portion of the mask pattern portion.

[0037]

According to the invention, a plurality of inspection pattern portions having the same pattern as at least a part of a mask pattern portion, are disposed inside and/or outside an area of the mask pattern portion of the exposure pattern or mask, and one or more of the inspection patterns are compared with at least the portion of the mask pattern portion. Accordingly, the mask pattern portion can be compared directly with the inspection pattern or patterns so that the pattern inspection precision can be improved, comparison inspection by the Die to Die method among others becomes possible, and comparison inspection can be performed with ease and at a high reliability by using a general wafer defect inspection apparatus.

[0038]

Furthermore, since a plurality of inspection pattern portions having patterns suitable for comparison inspection can be disposed inside and/or outside an area of the mask pattern portion of the exposure pattern or mask, the degree of freedom of the layout of inspection patterns can be improved more than the layout of dies having the same pattern in the mask pattern portion. Still further, the comparison inspection precision can be improved by increasing the number of inspection patterns.

Brief Description of the Drawings

[0039]

The above and other objects, features and advantages of the present invention will become more apparent from the following description of the presently preferred exemplary embodiments of the present invention taken in conjunction with the accompanying drawings, in which:

[0040]

Figs. 1A, 1B and 1C are schematic plan views of stencil masks having dummy inspection pattern portion or portions according to a first embodiment of the present invention;

[0041]

Figs. 2A, 2B and 2C are schematic plan views of other stencil masks according to the first embodiment;

[0042]

Figs. 3A, 3B and 3C are schematic plan views of other stencil masks according to the first embodiment;

[0043]

Fig. 4A is a partially enlarged plan view of a stencil mask according to the first embodiment, and Fig. 4B is a cross

sectional view taken along line X-X' shown in Fig. 4A;

[0044]

Figs. 5A to 5C are cross sectional views illustrating stencil mask fabrication processes in sequence according to the first embodiment;

[0045]

Figs. 6A to 6C are cross sectional views illustrating stencil mask fabrication processes in sequence according to the first embodiment;

10 [0046]

Fig. 7 is a flow chart illustrating an exposure process using a stencil mask according to the first embodiment.

[0047]

Fig. 8 is a schematic plan view of a stencil mask having dummy inspection areas according to a second embodiment of the invention;

[0048]

Fig. 9 is a schematic plan view and its partially enlarged view of a DRAM memory area in a mask pattern portion according to the second embodiment;

20

[0049]

Fig. 10A is a schematic plan view of a conventional stencil mask, and Fig. 10B is a cross sectional view taken along line X-X' shown in Fig. 10A;

25

[0050]

Fig. 11 is a cross sectional view illustrating an exposure process using a conventional stencil mask;

[0051]

Fig. 12A is a plan view showing an example of an exposure pattern, Fig. 12B is a plan view of complementary mask patterns, and Fig. 12C is a plan view of overlaid

30

complementary masks, according to conventional techniques;
[0052]

Figs. 13A to 13C are cross sectional views sequentially illustrating conventional stencil mask
5 fabrication processes;
[0053]

Figs. 14A to 14C are cross sectional views sequentially illustrating conventional stencil mask fabrication processes; and
10 [0054]

Fig. 15 is a plan view showing a conventional stencil mask.

Description of the Preferred Embodiments
15 [0055]

According to the invention, in order to improve the reliability of comparison inspection, it is preferable to set the number of inspection pattern portions to a twofold or more of the number of areas of at least the portion of the mask
20 pattern.
[0056]

In order to facilitate the comparison inspection, it is preferable to dispose the inspection pattern portions near the mask pattern portion.
25 [0057]

The mask pattern portion is formed by forming through holes having a predetermined pattern through a thin film through which the exposure beam passes, and the inspection patterns are preferably formed in the form of recesses in order
30 to prevent the exposure beam from transmitting through the exposure pattern or mask.

[0058]

To this end, it is preferable that the mask pattern portion is formed by using the thin film and the inspection pattern portions are formed by using the thin film on a support substrate.

[0059]

At least the portion of the mask pattern portion and the inspection pattern portion or portions are optically detected and detected information is compared.

10 [0060]

Inspection of the mask pattern portion can be performed by a chip comparison inspection (inspection by the Die to Die method) or a cell comparison inspection (inspection by the Cell to Cell method).

15 [0061]

The manufacture conditions are preferably controlled by the result of the comparison inspection, in order to manufacture the exposure pattern or mask at a high precision.

[0062]

20 Preferred embodiments of the invention will be described specifically with reference to the accompanying drawings.

[0063]

First Embodiment

25 In this embodiment, as shown in Figs. 1A to 3C, a plurality of dummy inspection pattern portions 3 are disposed near to, or next to, a mask pattern portion 16 (membrane). The dummy inspection pattern portion 3 has the same pattern as that of the mask pattern portion 16, and the mask pattern portion 16 is defined in the central area of an Si wafer (support substrate) 6 constituting a stencil mask 7, for example, for

LEEPL (Low Energy E-beam Proximity Projection Lithography) .
[0064]

As shown in Figs. 4A and 4B, since each dummy inspection pattern portion 3 is used as a dummy for inspection
5 of the mask pattern portion 16, as will be later described, the dummy inspection pattern portion 3 is not necessary to have through holes formed through a thin film as in the case of the mask pattern portion 16. Instead, the dummy inspection pattern portion 3 may have recesses (excavated structures
10 through etching) having the same pattern as that of the mask pattern portion 16 and formed in partial regions on the Si wafer 6.

[0065]

The stencil mask 7 shown in Fig. 1A has two dummy
15 inspection pattern portions 3 formed on the Si wafer 6 next to, and to the right and left of, as viewed from an orientation mark 4, the mask pattern portion 16 in the central area of the Si wafer 6.

[0066]

20 With this layout, inspection by the Die to Die method can be performed on the Si wafer 6 through comparison of one mask pattern portion 16 with two dummy inspection pattern portions 3.

[0067]

25 Although the dummy inspection pattern portions 3 are drawn next to the mask pattern portion 16, as shown in Figs. 4A and 4B they are actually disposed spaced apart by a predetermined distance from the mask pattern portion 16 and a support column 10 is formed on the back side of the mask
30 pattern portion 16, in order to retain the mechanical strength of the stencil mask 7. Each quadrant of the mask pattern

portion 16 and dummy inspection pattern portions 3 is distinguishably indicated by narrow lines.

[0068]

5 The stencil mask 7 shown in Fig. 1B has two dummy inspection pattern portions 3 formed next to, and on the upper and lower sides of, as viewed from the orientation mark 4, the mask pattern portion 16 in the central area of the Si wafer 6.

[0069]

10 The stencil mask 7 shown in Fig. 1C has four dummy inspection pattern portions 3 next to, to the right and left of, and on the upper and lower sides of, as viewed from the orientation mark 4, the mask pattern portion 16 in the central area of the Si wafer 6.

15 [0070]

With this layout, defect can be more reliably inspected because one mask pattern portion 16 can be compared with four dummy inspection pattern portions 3.

[0071]

20 The stencil mask 7 shown in Fig. 2A has two mask pattern portions 16 next to, and to the right and left of, as viewed from the orientation mark 4, the mask pattern portion 16 in the central area of the Si wafer 6, and has two sets of three dummy inspection pattern portions next to, and on
25 the upper and lower sides of, the three mask pattern portions 16.

[0072]

30 With this layout, even if the mask pattern of each mask pattern portion 16 is the same or different, the defect inspection can be performed effectively relative to the upper and lower inspection pattern portions 3 at the number ratio

of 1 : 2.

[0073]

The stencil mask 7 shown in Fig. 2B has two mask pattern portions 16 next to, and on the upper and lower sides of, as viewed from the orientation mark 4, the mask pattern portion 16 in the central area of the Si wafer 6, and has two sets of three dummy inspection pattern portions 3 next to, and to the right and left of, the three mask pattern portions 16.

10 [0074]

With this layout, similar to the stencil mask 7 shown in Fig. 2A, even if the mask pattern of each mask pattern portion 16 is the same or different, the defect inspection can be performed effectively.

15 [0075]

The stencil mask 7 shown in Fig. 2C has four dummy inspection pattern portions 3 next to, on the upper and lower sides of, and to the right and left of, as viewed from the orientation mark 4, the mask pattern portion 16 in the central area of the Si wafer 6, and has four mask pattern portions 16 next to, on the diagonally upper right and left of, and on the diagonally lower right and left of, the central mask pattern portion 16.

[0076]

25 A ratio of the number of mask pattern portions 16 to the number of dummy inspection pattern portions 3 is 5 : 4. When the mask pattern portions 16 are to be sequentially inspected, the dummy inspection pattern portions 3 can be selected at the ratio of 1 : 2 or higher (e.g., 1 : 4).

30 [0077]

Furthermore, for example, only the central mask

pattern portion 16 may be used as an inspection object and the other mask pattern portions 16 are used as reserved mask pattern portions. In this case, even if the central mask pattern portion 16 has a low pattern precision and cannot be used practically, another reserved mask pattern portion 14 can be used in place of the defective mask pattern portion 16. It is therefore unnecessary to manufacture again a new stencil mask 7.

[0078]

The stencil mask 7 shown in Fig. 3A has two dummy inspection pattern portions 3 next to, on the diagonally upper right of, and on the diagonally lower left of, as viewed from the orientation mark 4, the mask pattern portion 16 in the central area of the Si wafer 6.

[0079]

With this layout, similar to the stencil masks shown in Figs. 1A and 1B, the defect inspection of the mask pattern of one mask pattern portion 16 can be performed by using two inspection dummy patterns 3.

[0080]

The stencil mask 7 shown in Fig. 3B has two dummy inspection pattern portions 3 next to, on the diagonally upper left of, and on the diagonally lower right of, as viewed from the orientation mark 4, the mask pattern portion 16 in the central area of the Si wafer 6.

[0081]

The stencil mask 7 shown in Fig. 3C has four dummy inspection pattern portions 3 next to, on the diagonally upper right and left of, and on the diagonally lower right and left of, as viewed from the orientation mark 4, the mask pattern portion 16 in the central area of the Si wafer 6.

[0082]

With this layout, similar to the stencil mask shown in Fig. 1C, the defect inspection of the mask pattern of one mask pattern portion 16 can be performed by using four inspection dummy patterns 3, resulting in a more accurate defect inspection.

[0083]

As shown in the plan view of Fig. 4A and the cross sectional view of Fig. 4B taken along line X-X' shown in the plan view, each of the stencil masks 7 described above, e.g., the stencil mask 7 shown in Fig. 1A, has the mask pattern portion 16 having first to fourth quadrants 2A, 2B, 2C and 2D and made of a membrane or thin film 1 (corresponding to the previously described membrane 51). In order to make it easy to understand, only several pattern openings 15 are drawn in a simplified shape.

[0084]

The dummy inspection pattern portions 3 are disposed next to, and to the right and left of, the mask pattern portion 16 and formed in the membrane 1 on the Si substrate 6. The dummy inspection pattern portion 3 has inspection pattern openings 17 in the form of recesses having the same pattern as that of the mask pattern portion 16.

[0085]

The membrane 1 having the mask pattern portion 16 is supported by the Si wafer (support substrate) 6 via an SiO₂ film 5 having an opening 8 formed around the pattern openings 15, the Si wafer 6 has an opening 9 larger than that of the opening 8 of the SiO₂ film. Since the membrane 1 is a thin film and is liable to breakage, the membrane 1 is reinforced by disposing a support column 10 on the membrane 1 on the side

of the opening 8.

[0086]

The dummy inspection pattern portions 3 disposed next to the mask pattern portion 16 don't have a thin film membrane structure, but they have the excavated structures formed by etching the membrane 1 on the support substrate Si wafer 6 down to the surface of the SiO₂ film 5 to form the inspection pattern openings 17 having the same pattern as that of the mask pattern portion 16.

10 [0087]

If the thickness of the membrane 1 is, for example, 0.5 μm , it is preferable to set the depth of the openings 17 in the dummy inspection pattern portion 3 to 0.5 μm same as the thickness of the membrane 1 in order to use the same etching conditions (i.e., the same patterning precision) as those for the comparison inspection openings 15.

[0088]

The structure made of only the thin film membrane 1 is only in the mask pattern portion 16, and the dummy inspection pattern portions 3 are supported by the Si wafer 6. When an electron beam is emitted, the incident beam to the inspection pattern openings 17 of the dummy inspection pattern portions 3 is intercepted by the Si wafer 6 and the like, thus the beam does not transmit through the Si wafer 6. Accordingly, the stencil mask 7 has a strong mechanical strength and can prevent unnecessary transmission of an electron beam.

25 [0089]

Next, the manufacture processes for the stencil mask 7 will be described by way of example with reference to Figs. 5A to 6C. First, as shown in Fig. 5A, on an Si wafer (support substrate) 6, an SiO₂ film 5 and a membrane 1 made of Si or

SiC are sequentially deposited to predetermined thicknesses.
[0090]

As shown in Fig. 5B, a resist layer 27 having a predetermined pattern is formed on the Si wafer 6. A partial
5 region of the Si wafer 6 is removed down to the surface of the SiO₂ film 5 by dry etching to form an opening 9 and a support column 10.

[0091]

As shown in Fig. 5C, after the resist pattern 27
10 is removed, by using the Si wafer 6 and support column 10 as a mask, a partial region of the SiO₂ film 5 is removed down to the surface of the membrane 1 by dry etching to form an opening 8.

[0092]

As shown in Fig. 6A in the up-side-down state of
15 Fig. 5C, a resist layer 27 is formed on the membrane 1 and processed to have a predetermined pattern.

[0093]

More specifically, openings 18 are formed through
20 the resist pattern 27 in such a manner that a mask pattern portion 16 is formed in a partial area of the membrane 1 above the openings 8 and 9 and that two dummy inspection pattern portions 3 are formed on the Si wafer 6 almost next to the mask pattern portion 16.

25 [0094]

Next, as shown in Fig. 6B, by using the resist pattern 27 as a mask, the membrane 1 is dry etched to form through holes in the area corresponding to the mask pattern portion 16 to thereby form mask pattern openings 15 and at the same
30 time to form inspection pattern openings or recesses 17 in the dummy inspection pattern portions 3, the recesses 17

reaching the surface of the SiO₂ film 5 and having the same pattern as that of the mask pattern portion 16.

[0095]

5 Thereafter, as shown in Fig. 6C, the resist pattern 27 on the membrane 1 is removed so that a stencil mask 7 shown in Fig. 4B can be formed.

[0096]

Fig. 7 is a flow chart illustrating an exposure process using the stencil mask 7 of this embodiment.

10 [0097]

First, a stencil mask 7 such as shown in Fig. 4 is formed. In this case, the mask pattern portion 16 and dummy inspection pattern portions 3 are formed at the same time (Step 1).

15 [0098]

Next, the defect inspection of the mask pattern portion 16 is performed through comparison inspection by the Die to Die method relative to the dummy inspection pattern portions 3 (Step 2).

20 [0099]

If this defect inspection suggests any necessary modification of the pattern of the mask pattern portion 16, this information is fed back to the manufacture of the stencil mask 7 so that the stencil mask manufacture conditions can be controlled. If the modification is not necessary, the next process is executed (Step 3).

[0100]

Any defect of the mask pattern portion 16 can be found by the comparison inspection that the mask pattern portion 16 and dummy inspection pattern portions 3 are imaged at the same time to compare pattern images formed by light

30

reflected from these pattern portions.

[0101]

Next, an electron beam resist exposure is performed by using the stencil mask 7 which is unnecessary for the
5 modification (Step 4) and then a resist development process (Step 5) is performed to thereafter terminate the exposure process.

[0102]

As described above, according to the embodiment,
10 a plurality of dummy inspection pattern portions 3 having the same pattern as that of the mask pattern portion 16 are disposed next to, and in an area other than that of, the mask pattern portion 16. The mask pattern portion 16 is compared with the dummy inspection pattern portions 3. Since the mask pattern
15 portion 16 can be compared directly with the dummy inspection pattern portions 3 next to the mask pattern portion 16, the comparison inspection can be performed at a high precision.

[0103]

A plurality of dummy inspection pattern portions
20 3 having the same pattern as that of the mask pattern portion 16 are disposed on the Si wafer 6 in the area different from the mask pattern portion 16. The degree of freedom of the layout of dummy inspection pattern portions 3 can therefore be expanded and the number of dummy inspection pattern portions
25 3 can be increased, so that the precision of the comparison inspection can be improved.

[0104]

Since the mask pattern portion 16 and dummy inspection pattern portions 3 of the stencil mask 7 are formed
30 at the same time, the manufacture conditions are almost the same. Therefore, the pattern shapes of the mask pattern

portion 16 and dummy inspection pattern portions 3 are almost the same so that the precision of the comparison inspection is improved and the comparison inspection can be performed only by one stencil mask 7.

5 [0105]

It may be considered that a plurality of same stencil masks are formed and used as dummy stencil masks. An original stencil mask is compared with these dummy stencil masks to perform the comparison inspection by the Die to Die method. 10 With this method, however, since it is difficult to manufacture a plurality of stencil masks under the same manufacture conditions, each stencil mask has an in-plane irregular pattern. It is therefore difficult to manufacture a plurality of same stencil masks.

15 [0106]

According to the embodiment, a plurality of dummy inspection pattern portions 3 are disposed next to the mask pattern portion 16 made of only the membrane 1, so that the wafer defect inspection by the Die to Die method becomes 20 possible. It is therefore possible to inspect an LEEPL stencil mask 7 with an ordinary wafer defect inspecting apparatus with ease and at a good reliability. A die is one chip of the mask pattern portion 16, and the dummy inspection pattern portion having the same pattern as that of the mask pattern portion 25 16 is also a die corresponding to one chip.

[0107]

It is important that two or more dummy inspection pattern portions 3 are formed for each mask pattern portion 16 to have a number ratio of 1 : 2 or larger. If one dummy 30 inspection pattern portion 3 is formed for one mask pattern portion 16 (a number ratio of 1 : 1), the comparison inspection

is difficult to judge whether the defect is contained in the mask pattern portion 16 or in the dummy inspection pattern portion 3. By forming at least two dummy inspection pattern portions 3 for one mask pattern portion 16, it becomes apparent
5 that the precision (or probability) of defect detection of the mask pattern portion 16 can be improved.

[0108]

The dummy inspection pattern 3 has the recesses of the excavated structures formed by etching the membrane 1 above
10 the Si wafer 6 to have a predetermined pattern. Therefore, the Si wafer 6 helps maintain the mechanical strength of the stencil mask 7, and in addition the Si wafer 6 prevents the exposure electron beam from transmitting through the dummy inspection pattern portion 3 during the exposure process.

15 [0109]

Second Embodiment

The second embodiment as shown in Figs. 8 and 9 is similar to the first embodiment, excepting that not only the chip comparison inspection (inspection by the Die to Die method) through comparison between the mask pattern portion
20 16 and dummy pattern portions 3 in constant with the mask pattern portion 16 can be performed, but also a cell comparison inspection (inspection by a "Cell to Cell" method) in the mask pattern portion 16 can be performed.

25 [0110]

In the mask pattern portion 16 shown in Fig. 8, pattern openings are formed, for example, for DRAM (Dynamic Random Access Memory) devices constituted of memory cell groups and for LOGIC circuit devices. Defect of memory cell groups
30 of the DRAM devices having, for example, repetitive patterns is inspected through comparison by the Cell to Cell method

in each DRAM device. Defect of the LOGIC devices having no repetitive patterns is inspected through comparison by the Die to Die method that compares with the dummy LOGIC patterns of the right and left dummy inspection pattern portions 3 in
5 the mask pattern portion 16.

[0111]

More specifically, defect of memory cell groups of the DRAM devices having repetitive patterns of the mask pattern portion 16 is inspected through cell comparison (inspection
10 by the Cell to Cell method) between memory cells within each DRAM device. Since even fine memory cells can be inspected, the inspection sensitivity can be improved. It is also possible to inspect defect of the DRAM devices or LOGIC devices in the mask pattern portion 16 through comparison inspection
15 by the Die to Die method, by referring to the right and left dummy DRAM devices or dummy LOGIC devices in the dummy inspection pattern portions 3.

[0112]

Fig. 9 is a schematic diagram illustrating
20 comparison inspection by the Cell to Cell method and showing a partial enlarged view of a memory portion 20 of a DRAM device. The memory area 20 has a number of cells having the same pattern and disposed in a matrix shape. As schematically shown in an enlarged view, four types of dummy cell patterns 13a, 13b,
25 13c and 13d and four types of candidate cell patterns (to be inspected) 12a, 12b, 12c and 12d are alternately disposed at a predetermined distance or pitch. These patterns are all formed within the mask pattern portion 16.

[0113]

30 Defect comparison inspection of a candidate cell pattern, e.g., candidate cell pattern 12a, in the memory

portion 20, can be performed by using, for example, two dummy cell patterns 13a having the same pattern in the same row. Since the dummy cell patterns and candidate cell patterns are disposed at the predetermined pitch, comparison inspection
5 between corresponding patterns can be performed reliably by designating coordinates of the patterns. Defect inspection for the other candidate cell patterns 12b, 12c and 12d can be performed in a similar manner.

[0114]

10 Since defect inspection by the Cell to Cell method is possible for memory cells in each DRAM device within the mask pattern portion 16, the pattern inspection precision can be improved more than the Die to Die method. The cell patterns judged good by the comparison inspection are used as masks.
15 It is obvious that dummy cell patterns can be used as real patterns.

[0115]

Although DRAMs are used by way of example, a display may be used. In this case, the pattern of each pixel in an
20 image area can be subjected to comparison inspection in a similar manner.

[0116]

In addition to the functions and advantages described above, the second embodiment also has the functions
25 and advantages similar to those of the first embodiment.

[0117]

The embodiments described above can be modified in various ways based upon the technical concept of the present invention.

30 [0118]

For example, the shape, number, size, layout

position and the like of dummy inspection pattern portions
can be selected as desired by considering the mask pattern
portion. As described earlier, although the dummy inspection
pattern portion may be disposed outside the mask pattern
5 portion or inside and outside the mask pattern portion, it
may be disposed only inside the mask pattern.

[0119]

It is preferable to use a number of dummy inspection
pattern portions in order to improve the inspection precision
10 of comparison with the mask pattern portion. Comparison
inspection using the dummy inspection patterns may adopt the
Die to Die method or the Cell to Cell method, together with
the Die to Data method.

[0120]

15 The stencil mask is not limited only to LEEPL, but
stencil masks for EPL or IPL may also be used. The invention
may be applied to various exposure patterns of electrodes,
wirings, dielectric films and the like. In addition to the
stencil masks for LEEPL, EPL and IPL, exposure masks (reticles)
20 of other types may also be formed with the above-described
dummy inspection patterns.

[0121]

Finally, the embodiments and examples described above
are only examples of the present invention. It should be noted
25 that the present invention is not restricted only to such
embodiments and examples, and various modifications,
combinations and sub-combinations in accordance with its
design or the like may be made without departing from the scope
of the present invention.